


Cordes tordues Twisted ropes Cuerdas cableadas

Polysteel



Naberan[®]

www.naberan.com



Ø	Circ. Pouce Circ. Inch Circ. Pulgadas	Metrage Runnage Metraje		Charge rupture Breaking Strength Carga Rotura	
		Kg/100m	lb/100ft	kfg	lb
6	3/4"	1.65	1.20	1.770	1.690
8	1"	3.00	2.00	1.360	2.990
10	1 1/4"	4.40	3.00	2.035	4.480
12	1 1/2"	6.40	4.40	2.900	6.380
14	1 3/4"	8.50	6.10	3.905	8.600
16	2"	11.50	7.70	4.910	10.810
18	2 1/4"	15.00	10.00	6.305	13.880
20	2 1/2"	18.00	12.10	7.600	16.740
22	2 3/4"	21.50	14.80	8.905	19.610
24	3"	26.00	17.50	10.490	23.100
26	3 1/4"	30.00	20.50	12.320	27.130
28	3 1/2"	36.00	23.80	13.910	30.630
30	3 3/4"	40.00	27.20	16.070	35.390
32	4"	46.00	30.90	17.540	38.630
36	4 1/2"	59.00	39.30	22.080	48.630
40	5"	72.00	48.00	26.860	59.160
44	5 1/2"	88.00	59.10	31.780	70.000
48	6"	104.00	69.80	37.180	81.890
52	6 1/2"	122.00	82.00	43.195	95.140
56	7"	142.00	95.30	49.380	108.760
60	7 1/2"	162.00	109.50	56.680	124.480

Naberan sareak sl

Mutrikuko Industrialdea 15 zb
20830 Mutriku (Gipuzkoa) Spain
Telf: +34943195122 Fax: +34943195125
naberan@naberan .com

J5

Naberan France

Avenue de la republique
29730 Le Guilvinec, France
Telf: +33(0)298582739 Fax: +33(0)298580475
naberan.france@wanadoo.fr

Cordes tordues Twisted ropes Cuerdas cableadas



Naberan[®]

www.naberan.com

Polyethylene / Polyéthylène / Polietileno



Ø	Circ. Pouce Circ. Inch Circ. Pulgadas	Metrage Runnage Metraje		Charge Rupture Breaking strength Carga Rotura	
		Kg/100m	lb/100ft	kfg	lb
4	1/2"	0.81	0.54	200	440
5	5/8"	1.30	0.87	290	640
6	3/4"	1.80	1.23	400	880
8	1"	3.25	2.20	700	1.540
10	1 1/4"	5.00	3.30	1.090	2.400
12	1 1/2"	7.00	4.80	1.540	3.390
14	1 3/4"	9.50	6.40	2.090	4.600
16	2"	13.00	8.60	2.800	6.170
18	2 1/4"	16.00	10.80	3.470	7.640
20	2 1/2"	20.00	13.40	4.280	9.430
22	2 3/4"	24.00	16.30	5.080	11.190
24	3"	29.50	19.80	6.100	13.440
26	3 1/4"	33.00	22.00	6.940	15.290
28	3 1/2"	39.00	26.40	8.200	18.060
30	3 3/4"	46.00	30.90	9.490	20.900
32	4"	52.50	35.20	10.700	23.570
36	4 1/2"	66.00	44.30	13.460	29.650
40	5"	78.50	52.70	16.320	35.950
44	5 1/2"	95.00	63.80	19.630	43.240
48	6"	115.00	77.20	22.850	50.330
52	6 1/2"	135.00	90.60	26.420	58.195
56	7"	157.00	105.40	30.400	66.960
60	7 1/2"	180.00	128.00	34.480	75.950

Naberan sareak sl

Mutrikuko Industrialdea 15 zb
20830 Mutriku (Gipuzkoa) Spain
Telf: +34943195122 Fax: +34943195125
naberan@naberan.com

J6

Naberan France

Avenue de la republique
29730 Le Guilvinec, France
Telf: +33(0)298582739 Fax: +33(0)298580475
naberan.france@wanadoo.fr

Cordes tordues Twisted ropes Cuerdas cableadas



Naberan®

www.naberan.com

NYLON



Ø	Circ. Pouce. Circ. Inch Circ. Pulgadas	Metrage Runnage Metrage		Charge rupture Breaking strength Carga Rotura	
		Kg/100m	lb/100ft	kfg	lb
4	1/2"	1.05	0.7	320	700
5	5/8"	1.65	1.1	500	1.100
6	3/4"	2.25	1.5	750	1.650
8	1"	4.00	2.7	1.350	2.970
10	1 1/4"	6.20	4.2	2.080	4.580
12	1 1/2"	8.90	6.0	3.000	6.600
14	1 3/4"	12.20	8.2	4.100	9.030
16	2"	15.80	10.6	5.300	11.675
18	2 1/4"	20.00	13.4	6.700	14.760
20	2 1/2"	24.50	16.4	8.300	18.280
22	2 3/4"	30.00	20.1	10.000	22.030
24	3"	35.50	23.8	12.000	26.430
26	3 1/4"	42.00	28.2	14.000	30.840
28	3 1/2"	48.50	32.6	15.800	34.800
30	3 3/4"	55.50	37.3	17.800	39.210
32	4"	63.00	42.3	20.000	44.050
36	4 1/2"	80.00	53.7	24.800	54.625
40	99.00	66.5	30.000	66.080	
44	5 1/2"	120.00	81.0	35.800	78.850
48	6"	142.00	95.0	42.200	92.510
52	6 1/2"	166.00	112.0	48.800	107.490
56	7"	193.00	130.0	56.000	123.350
60	7 1/2"	221.00	148.0	63.800	140.500
64	8"	252.00	169.0	72.000	158.600
72	9"	319.00	214.0	90.000	198.200
80	10"	394.00	264.0	110.000	242.300

Naberan sareak sl

Mutrikuko Industrialdea 15 zb
20830 Mutriku (Gipuzkoa) Spain

Telf: +34943195122 Fax: +34943195125

naberan@naberan.com

J7

Naberan France

Avenue de la republique
29730 Le Guilvinec, France

Telf: +33(0)298582739 Fax: +33(0)298580475

naberan.france@wanadoo.fr

Cordes tordues Twisted ropes Cuerdas cableadas

POLYESTER



Naberan[®]
www.naberan.com



Ø	Circ Pouce. Circ. Inch Circ. Pulgadas	Metrage Runnage Metraje		Charge rupture Braking strength Carga Rotura	
		Kg/100m	lb/100ft	kfg	lb
4	1/2"	1.18	0.7	0.79	650
5	5/8"	1.85	1.1	1.24	1.020
6	3/4"	2.70	1.5	1.81	1.245
8	1"	4.80	2.7	3.22	2.245
10	1 1/4"	7.60	4.2	5.10	3.500
12	1 1/2"	11.00	6.0	7.39	5.010
14	1 3/4"	14.80	8.2	9.93	7.005
16	2"	19.50	10.6	13.08	8.945
18	2 1/4"	24.50	13.4	16.46	11.190
20	2 1/2"	30.50	16.4	20.34	14.000
22	2 3/4"	36.70	20.1	24.70	16.585
24	3"	43.70	23.8	29.30	20.130
26	3 1/4"	51.20	28.2	34.40	23.590
28	3 1/2"	59.40	32.6	40.00	26.960
30	3 3/4"	68.20	37.3	45.80	30.110
32	4"	77.80	42.3	52.30	34.605
36	4 1/2"	98.20	53.7	65.80	42.690
40	5"	121.50	30.000	81.60	52.800
44	5 1/2"	146.80	81.0	98.60	62.690
48	6"	175.00	95.0	117.60	73.920
52	6 1/2"	205.00	112.0	137.60	86.280
56	7"	238.00	130.0	159.90	98.635
60	7 1/2"	273.00	148.0	183.40	109.870
64	8"	311.00	169.0	208.80	127.610
72	9"	393.00	214.0	263.90	158.845
80	10"	485.00	264.0	325.60	194.790

Naberan sareak sl

Mutrikuko Industrialdea 15 zb
20830 Mutriku (Gipuzkoa) Spain
Telf: +34943195122 Fax: +34943195125
naberan@naberan .com

J8

Naberan France

Avenue de la republique
29730 Le Guilvinec, France
Telf: +33(0)298582739 Fax: +33(0)298580475
naberan.france@wanadoo.fr

Cordes tordues Twisted ropes Cuerdas cableadas



Naberan[®]

www.naberan.com

Polypropylène multifilament
Polypropylene multifilament
Polipropileno multifinamento



Ø	Circ. Pouce. Circ. Inch Circ. Pulgadas	Metrage Runnage Metrage		Charge rupture Breaking strength Carga Rotura	
		Kg/100m	lb/100ft	kfg	lb
4	1/2"	0.75	0.50	235	518
5	5/8"	1.10	0.74	360	793
6	3/4"	1.70	1.20	600	1.320
8	1"	3.00	2.00	1.060	2.335
10	1 1/4"	4.50	3.00	1.560	3.430
12	1 1/2"	6.50	4.40	2.220	4.880
14	1 3/4"	9.00	6.10	3.050	6.720
16	2"	11.50	7.70	3.780	8.320
18	2 1/4"	14.80	10.00	4.820	10.610
20	2 1/2"	18.00	12.10	5.800	12.785
22	2 3/4"	22.00	14.80	6.950	15.320
24	3"	26.00	17.50	8.130	17.910
26	3 1/4"	30.50	20.50	9.400	20.715
28	3 1/2"	35.50	23.80	10.700	23.570
30	3 3/4"	40.50	27.20	12.200	26.900
32	4"	46.00	30.90	13.500	29.730
36	4 1/2"	58.50	39.30	16.900	37.270
40	5"	72.00	48.30	20.500	45.150
44	5 1/2"	88.00	59.10	24.640	54.260
48	6"	104.00	69.80	28.600	63.000
52	6 1/2"	122.00	82.00	33.100	72.910
56	7"	142.00	95.30	37.840	83.350
60	7 1/2"	163.00	109.50	43.300	95.310

Naberan sareak sl

Mutrikuko Industrialdea 15 zb
20830 Mutriku (Gipuzkoa) Spain
Telf: +34943195122 Fax: +34943195125
naberan@naberan.com

J9

Naberan France

Avenue de la republique
29730 Le Guilvinec, France
Telf: +33(0)298582739 Fax: +33(0)298580475
naberan.france@wanadoo.fr

Cordes Tressées Braided ropes Cuerdas trenzadas



Naberan[®]
www.naberan.com

NYLON

Ø	Poids Weight Peso.	Charge rupture Breaking strength Carga Rotura
mm	100 mts	
6	2.25	750
8	4.00	1.350
10	6.20	2.080
12	8.90	3.000
14	12.20	4.100
16	15.80	5.300
18	20.00	6.700
20	24.50	8.300
22	30.00	10.000
24	35.50	12.000
26	42.00	14.000
28	48.50	15.800
30	55.50	17.800
32	63.00	20.000



POLYESTER

Ø	Poids Weight Peso	Charge rupture Breaking strength Carga Rotura
mm	100 mts	
6	12.70	565
8	4.80	1.020
10	7.60	1.590
12	11.00	2.275
14	14.80	3.180
16	19.50	4.060
18	24.50	5.080
20	30.50	6.355
22	36.70	7.620
24	43.70	9.140
26	51.20	10.710
28	59.40	12.240
30	68.20	13.670
32	77.80	15.700

Naberan sareak sl

Mutrikuko Industrialdea 15 zb
20830 Mutriku (Gipuzkoa) Spain
Telf: +34943195122 Fax: +34943195125
naberan@naberan .com

J10

Naberan France

Avenue de la republique
29730 Le Guilvinec, France
Telf: +33(0)298582739 Fax: +33(0)298580475
naberan.france@wanadoo.fr

Aussières tressés Mooring ropes Estachas



Naberan[®]
www.naberan.com

Polysteel

Ø	Circ. Pouce Circ. Inch Circ. Pulgadas	Metrage Runnage Metrage		Charge rupture Breaking strength Carga Rotura	
		Kg/100 m	lb/100 ft	kfg	lb
40	5"	72.0	48.3	26.860	59.160
44	5 1/2"	88.0	59.1	31.780	70.000
48	6"	104.0	69.8	37.180	81.890
52	6 1/2"	122.0	82.0	43.195	95.140
56	7"	142.0	95.3	49.380	108.760
60	7 1/2"	163.0	109.5	56.680	124.840
64	8"	185.0	124.0	64.140	141.270
68	8 1/2"	209.0	140.7	72.062	158.720
72	9"	234.0	157.0	80.225	176.700
80	10"	290.0	195.0	99.050	218.170

Polypropylène Raphia Polypropylene split Film Itsasplus Polipropileno Rafia

Ø	Circ. Pouce. Circ. Inch Circ. Pulgadas	Metrage Runnage Metrage		Charge rupture Breaking strength Carga Rotura	
		Kg/100 m	lb/100 ft	kfg	lb
40	5"	72.0	48.3	20.500	45.150
44	5 1/2"	89.0	59.1	24.640	54.260
48	6"	105.0	69.8	28.600	63.000
52	6 1/2"	120.0	82.0	33.100	72.910
56	7"	140.0	95.3	37.840	83.350
60	7 1/2"	165.0	109.5	43.300	95.310
64	8"	185.0	124.0	48.960	107.840
72	9"	235.0	157.0	61.470	135.410
80	10"	290.0	195.0	75.600	166.540



Nylon

Ø	Circ. Pouce. Circ. Inch. Circ. Pulgadas	Metrage Runnage Metrage		Charge rupture Breaking strength Carga Rotura	
		Kg/100 m	lb/100 ft	kfg	lb
40	5"	99.0	66.5	30.000	66.080
44	5 1/2"	120.0	81.0	35.800	78.850
48	6"	142.0	95.0	42.000	92.510
52	6 1/2"	166.0	112.0	48.800	107.490
56	7"	193.0	130.0	56.000	123.350
60	7 1/2"	221.0	148.0	63.800	140.500
64	8"	252.0	169.0	72.000	158.600
72	9"	319.0	214.0	90.000	198.200
80	10"	394.0	264.0	110.000	242.300

Naberan sareak sl

Mutrikuko Industrialdea 15 zb
20830 Mutriku (Gipuzkoa) Spain
Telf: +34943195122 Fax: +34943195125
naberan@naberan.com

J11

Naberan France

Avenue de la republique
29730 Le Guilvinec, France
Telf: +33(0)298582739 Fax: +33(0)298580475
naberan.france@wanadoo.fr

Cordage dynema
 Dynema rope
 Cuerda dinema



Naberan[®]
 www.naberan.com



Ø	Circ. Pouce. Circumf. (inches) Circ. Pulgadas	poids Weight Peso (Kg/100 m)	SK 60	SK 75
			Charge rupture Breaking strength Carga rotura (Metr. Tons)	Charge rupture Breaking strength Carga rotura (Metr. Tons)
10	1 ¼	5,7	7.2	9.1
12	1 ½	8	10.4	13.0
14	1 ¾	11	14.1	17.6
16	2	14	17.8	22.2
18	2 ¼	18	22.4	28.0
20	2 ½	22	27.7	34.6
22	2 ¾	26	33.6	42.0
24	3	31	39.8	49.8
26	3 ¼	36	47.0	58.8
28	3 ½	42	54.4	68.1
30	3 ¾	48	62.5	78.1
32	4	55	71.5	89.4
34	4 ¼	62	80.5	100.6
36	4 ½	69	89.0	111.0
38	4 ¾	77	98.5	123.0
40	5	86	108.0	136.0
42	5 ¼	94	120.0	148.0
44	5 ½	104	132.0	168.0
46	5 ¾	113	144.0	182.0
48	6	123	156.0	195.0
50	6 ¼	138	168.0	203.0
52	6 ½	150	180.0	215.0

Naberan sareak sl

Mutrikuko Industrialdea 15 zb
 20830 Mutriku (Gipuzkoa) Spain
 Telf: +34943195122 Fax: +34943195125
 naberan@naberan .com

J12

Naberan France

Avenue de la republique
 29730 Le Guilvinec, France
 Telf: +33(0)298582739 Fax: +33(0)298580475
 naberan.france@wanadoo.fr